

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification <sup>7</sup> : B29D 30/10, 30/18, B60C 15/05	A1	(11) International Publication Number: <b>WO 00/26014</b> (43) International Publication Date: 11 May 2000 (11.05.00)
--	----	--

(21) International Application Number: PCT/EP99/07962

(22) International Filing Date: 20 October 1999 (20.10.99)

(30) Priority Data:

98830662.7

30 October 1998 (30.10.98)

EP

60/114,158

29 December 1998 (29.12.98)

US

(71) Applicant (for all designated States except US): PIRELLI PNEUMATICI S.P.A. [IT/IT]; Viale Sarca, 222, I-20126 Milano (IT).

(72) Inventor; and

(75) Inventor/Applicant (for US only): CARETTA, Renato [IT/IT]; Viale dei Tigli, 16, I-21013 Gallarate (IT).

(74) Agent: TANSINI, Elio, Fabrizio; Bugnion S.p.A., Viale Lancetti, 19, I-20158 Milano (IT).

(81) Designated States: BR, CN, JP, KR, RU, TR, US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).

Published

With international search report.

(54) Title: METHOD FOR MANUFACTURING A CARCASS STRUCTURE FOR VEHICLE TYRES, AND A CARCASS STRUCTURE OBTAINED THEREBY

(57) Abstract

A first carcass ply (3a) is manufactured by laying down onto a toroidal support (11), a first and a second series of strip-like sections (13, 14) cut to size from a continuous strip-like element (2a) and each comprising longitudinal thread-like elements (17) incorporated into a layer of elastomer material (20). Sections (13) of the first series are sequentially laid down at a given circumferential distance from each other, to form side portions (13a, 14a) to the end flaps of which first primary portions (4a) of respective reinforcing structures (4) at the beads are applied. Sections of the second series (14) are each interposed between two sections of the first series (13), with the respective end flaps (14a) overlapping the primary portions (4a) of the annular structures (4). A second ply (3b) is manufactured in the same manner as the first ply, with a third and a fourth series of strip-like sections (15, 16) disposed in a crossed orientation relative to those of the first carcass ply and overlapping second primary portions of the annular reinforcing structures (4) on opposite sides. Additional portions (24) of the annular structures are applied to the end flaps (20a) of sections (14) belonging to the second series.

